



**JLW-2070-1**

**Bi-Directional Filament Tape**

Physical Properties	Standard	Metric	Test Method	
Reinforcement	Fiberglass			
Adhesive	Hot Melt Adhesive			
Backing	PET			
Color	Clear			
Total Thickness	5.5 mils	0.14 mm	ASTM D-3652	GB/T7125
Peel Adhesion 90°	65 oz/in	18 N/25mm	ASTM D-3330	GB/T2792
Holding Power	10±3h	10±3h	ASTM D-3654	GB/T4851
Tensile strength	124 lbs/in	550 N/25mm	ASTM D-3759	GB/T7753
Elongation at Break	3-5%	3-5%	ASTM D-3759	GB/T7753
Service Tem.--Mini	23°F	-5°C	BC/BD-220SE	BC/BD-220SE
Service Tem.--Max	140°F	60°C	DHG-9055A	DHG-9055A

**Description:**

JLW-2070-1 Backed with PET film and reinforced with glass fiber. It's high strength bi-directional filament tape with high viscosity; suitable for bundling heavy objects and carton packing; general bundling; reinforced marine carton packaging; express-bag tear tape and so on.

**Performance Features:**

JLW-2070-1 is a transparent and high strength bi-directional filament tape. Glass fiber contributes higher tensile strength and improved hot melt adhesive delivers stronger adhesion; generating bi-directionally strengthened effect; high resistance to abrasion; impact resistance and high holding power.

**Storage Condition:**

It's recommended to store it in a clean, dry area to prevent packaging damage. Keep it away from volatile solvents. Storage temperature should be maintained between 4-26°C, with humidity levels between 40% - 50%. Rotating stock is advisable for optimal performance.

**Shelf Life:**

1 years from the date of shipment

The above properties and results obtained refer to the average values of laboratory testing carried out on the samples of JL3 product. JL3 does not guarantee testing accuracy and makes no guarantee of product performance, safety, or suitability, either expressed or implied, when used alone or in combination with other products. JL3 strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. JL3 assumes no responsibility for any damage or injury sustained as a result of the use of its products.

**Fujian Jialong Adhesive Tape Co.,Ltd.**

No. 11 Xiazhai Road, Jiulong Industrial Park, Hua An Economic Development Zone, Hua An, Zhangzhou, Fujian 363000 China.

Tel:+86 596-728-0001

info@jl3tape.com

http://www.jl3tape.com

